

# 104A, 104plus

## White Contrast Paint



BYCOTEST® 104A and 104plus are ready-to-use, rapid-drying white contrast paints. They produce a high-opacity, semi-matt, thin white film to enhance visible indications on dark-coloured test surfaces and improve probability of detection and sensitivity during visible magnetic particle inspections.

104A and 104plus can be used with all types of coloured and visible magnetic particles, and are suitable for use in both dry method and wet method magnetic particle inspection.

### BENEFITS

#### Maximise indication detection

- See indications more easily on the bright white surface which highlights indications while minimising glare and reflections.

#### Increase inspection speed

- Speed up inspections by applying a clean coat on the first pass, without bubbles or flakes.
- Dries evenly and quickly to create an optimal surface for faster indication formation.

#### Application versatility

- Comes in a convenient aerosol to take it with you wherever you go.
- Can be used with wet or dry method magnetic particles on virtually any part.
- Conforms to ISO 9934 specifications.

### FEATURES

- Bright white color
- High opacity
- Provides good background contrast
- Fast drying
- Convenient, ready to use formula
- Controlled application
- Strong surface adhesion
- Matte coating
- Very low toxicity
- Low in sulphur and halogens
- Contains no chlorinated hydrocarbons

### SPECIFICATION COMPLIANCE

- EN ISO 9934-2

### APPLICATIONS

#### Ideal for:

- Field testing
- Spot inspections
- In-service inspections

# 104A, 104plus

## COMPOSITION

Inert inorganic pigments and acrylic binder in a solvent blend. 104A's solvent base is ethanol; 104plus is based on acetone.

## PRODUCT PROPERTIES

<b>Form and colour</b>	White mobile liquid
<b>Sulphur content</b>	< 200 ppm
<b>Halogen content</b>	< 200 ppm

	<b>104A</b>	<b>104plus</b>
<b>Flash point</b>	-41°C	-40°C
<b>Density</b>	1.05 g/cm <sup>3</sup>	0.93 g/cm <sup>3</sup>
<b>Boiling point</b>	ca. 80°C	56°C

Like all Magnaflux materials, our contrast paints are closely controlled to ensure batch-to-batch consistency, optimum process control and inspection reliability.

## USER RECOMMENDATIONS

<b>NDT Method</b>	Magnetic Particle Testing, Visible, Wet Method
<b>Storage temperature</b>	10°C to 30°C
<b>Usage temperature</b>	-5°C to 50°C
<b>Coverage</b>	10 - 15m <sup>2</sup> per aerosol
<b>Visible magnetic inks</b>	103, 7HF, WB-27
<b>Cleaner/removers</b>	C10, SKC-S

## INSTRUCTIONS FOR USE

Clean the component before testing to provide a suitable test surface.

Shake the aerosol can to ensure the paint particles are evenly distributed.

Apply an thin, even film of the paint to the test surface by spraying. Allow to dry.

Apply magnetic particles to the test surface and observe any indications formed around leaks/defects. If the test material has a high retentivity, indications will remain visible; otherwise, the indications will slowly fade.

After inspection, demagnetise the test part before cleaning. The dried paint film can be removed using a wire brush or our C10 cleaner.

## PACKAGING AND PART NUMBERS

### 104A



008A172 (x 10)

### 104plus



008A173 (x 10)

## HEALTH AND SAFETY

Review all relevant health and safety information before using this product. For complete health and safety information, refer to the Safety Data Sheets, which are available at [www.magnaflux.eu](http://www.magnaflux.eu)